

FERRITE TOROIDAL CORES

MATERIAL 43				Permeability 850			
Core number	O.D. (inches)	I.D. (inches)	Hgt. (inches)	ℓ_e (cm)	A_e (cm) ²	V_e (cm) ³	A_L Value mh/1000 turns
FT-23 -43	.230	.120	.060	1.34	.021	.029	188
FT-37 -43	.375	.187	.125	2.15	.076	.163	420
FT-50 -43	.500	.281	.188	3.02	.133	.401	523
FT-50A -43	.500	.312	.250	3.68	.152	.559	570
FT-50B -43	.500	.312	.500	3.18	.303	.963	1140
FT-82 -43	.825	.516	.250	5.26	.246	1.290	557
FT-114 -43	1.142	.750	.295	7.42	.375	2.790	603
FT-140 -43	1.400	.900	.500	9.02	.806	7.280	952
FT-240 -43	2.400	1.400	.500	14.80	1.610	23.900	1240

MATERIAL 61				Permeability 125			
Core number	O.D. (inches)	I.D. (inches)	Hgt. (inches)	ℓ_e (cm)	A_e (cm) ²	V_e (cm) ³	A_L Value mh/1000 turns
FT-23 -61	.230	.120	.060	1.34	.021	.029	24.8
FT-37 -61	.375	.187	.125	2.15	.076	.163	55.3
FT-50 -61	.500	.281	.188	3.02	.133	.401	68.0
FT-50A -61	.500	.312	.250	3.68	.152	.559	75.0
FT-50B -61	.500	.312	.500	3.18	.303	.963	150.0
FT-82 -61	.825	.516	.250	5.26	.246	1.290	73.3
FT-114 -61	1.142	.750	.295	7.42	.375	2.790	79.3
FT-114A -61	1.142	.750	.545	7.42	.690	5.130	146.0
FT-140 -61	1.400	.900	.500	9.02	.806	7.280	140.0
FT-240 -61	2.400	1.400	.500	14.80	1.610	23.900	171.0

MATERIAL 67				Permeability 40			
Core number	O.D. (inches)	I.D. (inches)	Hgt. (inches)	ℓ_e (cm)	A_e (cm) ²	V_e (cm) ³	A_L Value mh/1000 turns
FT-23 -67	.230	.120	.060	1.34	.021	.029	7.8
FT-37 -67	.375	.187	.125	2.15	.076	.163	19.7
FT-50 -67	.500	.281	.188	3.02	.133	.401	22.0
FT-50A -67	.500	.312	.250	3.68	.152	.559	24.0
FT-50B -67	.500	.312	.500	3.18	.303	.963	48.0
FT-82 -67	.825	.516	.250	5.26	.246	1.290	22.4
FT-114 -67	1.142	.750	.295	7.42	.375	2.790	25.4
FT-140 -67	1.400	.900	.500	9.02	.806	7.280	45.0
FT-240 -67	2.400	1.400	.500	14.80	1.610	23.900	50.0

MATERIAL 68				Permeability 20			
Core number	O.D. (inches)	I.D. (inches)	Hgt. (inches)	ℓ_e (cm)	A_e (cm) ²	V_e (cm) ³	A_L Value mh/1000 turns
FT-23 -68	.230	.120	.060	1.34	.021	.029	4.0
FT-37 -68	.375	.187	.125	2.15	.076	.163	8.8
FT-50 -68	.500	.281	.188	3.02	.133	.401	11.0
FT-50A -68	.500	.312	.250	3.68	.152	.559	12.0
FT-82 -68	.825	.520	.250	5.26	.246	1.290	11.7
FT-114 -68	1.142	.750	.295	7.42	.375	2.790	12.7